

TECHNICAL DATA SHEET

EUROBENT 5300

Mechanically bonded composite, consisting of pulverized or granulated bentonite, embedded and fixed between two layers of geo-textile.

Mass per unit area (average)

Carrier Layer	PP Woven	100 g/m ²
Inlay	Na-Bentonite	5.300 g/m ²
Cover Layer	PP Nonwoven	200 g/m ²
Total Product Weight	ASTM D 5993	5.600 g/m ² (+/- 10 %)

Bentonite Properties

Montmorillonite Content	CUR 33	≥ 75 %
Swelling Capacity	ASTM D 5890	> 24 ml/2g
Moisture Content	DIN 18121-1 / 18121-2	max 12 %

Physical Properties of the Composite

Thickness	EN ISO 9863-1 / 9863-2	7,5 mm
Index Flux	ASTM D 5887	3,0 x 10 ⁻⁹ m ³ /m ² /s (6,0x10 ⁻⁹ m ³ /m ² /s)
Permeability	ASTM D 5887	1,8 x 10 ⁻¹¹ m/s (3,6 x 10 ⁻¹¹ m/s)
Tensile Strength	MD EN ISO 10319	10,4 kN/m (- 10 %)
	CD EN ISO 10319	8,5 kN/m (- 10 %)
CBR Puncture Strength	EN ISO 12236	1,8 kN (- 10 %)
Peel Strength	ASTM D 6496	50 N/10 cm (- 10 %)

Durability:

-cover in installation day

-durability 25 years at natural base and pH between 4 and 9 and temperature < 25°C.

Standard Roll Dimensions

Length / Width

(40 x 5,1) m

These data are average values derived from standard tests and are subject to usual product variation. The right is reserved to make changes without notice at any time.

Poland 58-100 Świdnica, ul. Kliczkowska 42

tel/fax +48 74 857 50 81

www.eurobent.com; office@eurobent.com

IX Wydział Gospodarczy KRS nr 0000297336

Wysokość kapitału zakładowego 50 000,00 zł

NIP 884-26-51-736; REGON 020678548

Deutsche Bank Polska S.A.

Pl. Grunwaldzki 36, PL-50-364 Wrocław

PL 10 1910 1048 2792 0378 4147 0001 - PLN

PL 80 1910 1048 2792 0378 4147 0002 - EUR

PL 53 1910 1048 2792 0378 4147 0003 - GBP

SWIFT: DEUTPLPX

*Sąd Rejonowy dla Wrocławia-Fabrycznej
we Wrocławiu*